



LOCTITE EA 460 AERO

Foaming Core Splice Adhesive

(KNOWN AS Hysol PL 460)

INTRODUCTION

LOCTITE EA 460 AERO is a foaming epoxy adhesive in paste form for easy extrusion through packaged cartridges. The adhesive expands and cures at temperatures from 250°F (121°C) to 350°F (177°C).

FEATURES

- Qualified to Boeing BMS 5-90, Type IV
- 30 day out time at 77°F (25°C)
- Closed cell expanding technology
- Resistance to sagging during cure
- Structural properties of a core splice film in paste form

USES

- Splicing honeycomb core edge closeouts
- Core fill

Typical Technical Data	LOCTITE EA 460 AERO
Type:	Modified Epoxy Paste
Form:	Available in 6 oz cartridges
Color:	Light Tan
Thickness:	0.050" ± 0.005" (1.27 ± 0.0127 cm)
Uncured Density:	58 lbs/ ft ³ (0.93 g/cc)
Volatiles:	0.76 % (2 hrs. at 217°F/103°C)
Weight:	.3 psf (1464 g/m ²)
Tg (DSC):	266°F (130°C)
Out Time:	30 days @ 77°F (25°C)
Shelf Life:	12 months @ 0°F (-18°C)

Performance Properties

Tube Shear Strength: 40-43 grams cured in 9" (23 cm) tube at 250°F (121°C) or 350°F (177°C).

Test Temp	Cured @ 250°F (121°C)	Cured @ 350°F (177°C)
-67°F (-55°C)	1750 psi (12.1 MPa)	2960 psi (20.4 MPa)
75°F (24°C)	1510 psi (10.4 MPa)	1682 psi (11.6 MPa)
250°F (121°C)	1170 psi (8.1 MPa)	----
350°F (177°C)	----	250 psi (1.7 MPa)

Typical technical data and performance properties given for reference only. Not for specification purposes.





LOCTITE EA 460 AERO

Foaming Core Splice Adhesive

(KNOWN AS Hysol PL 460)

Application Method

Allow product to warm to 75°F (24°C). If packaged in tubes, choose appropriate applicator nozzle. Apply to core for core fill, core splicing, or edge close out applications. Partially used containers may be returned to cold storage for reuse.

Cure

	77-250°F (25-121°C) <u>3.8°F (6°C)/min. rise</u>	77-350°F (25-177°C) <u>9.0°F (16°C)/min. rise</u>
Expansion, Ratio	2.1	3.0
Sag	0.15" (0.381 cm)	0.27" (0.69 cm)
	77-250°F (25-121°C) <u>3.8°F (6°C)/min. rise</u>	77-350°F (25-177°C) <u>9.0°F (16°C)/min. rise</u>
Exotherm	-----	464°F (240°C)
Cured Density	26.3 lbs/ft ³ (0.42 g/cc)	20.5 lbs/ft ³ (0.33 g/cc)

Recommended Cure: 90' @ 250°F (121°C) or 60' @ 350°F (177°C)

Clean-up

Uncured adhesive may be removed effectively with ketone solvents in well-ventilated areas. Avoid contaminating uncured parts. Consult solvent container label/MSDS for proper safety and handling procedures.

Storage

LOCTITE EA 460 AERO has a shelf life of 12 months @ 0°F (-18°C). The product has an out time of 30 days @ 77°F (25°C).

Handling Precautions

Do not handle or use until the Material Safety Data Sheet has been read and understood. For industrial use only.

DISPOSAL INFORMATION

Dispose of spent remover and paint residue per local, state and regional regulations. Refer to HENKEL TECHNOLOGIES MATERIAL SAFETY DATA SHEET for additional disposal information.





LOCTITE EA 460 AERO

Foaming Core Splice Adhesive

(KNOWN AS Hysol PL 460)

PRECAUTIONARY INFORMATION

General:

As with most epoxy based systems, use this product with adequate ventilation. Do not get in eyes or on skin. Avoid breathing the vapors. Wash thoroughly with soap and water after handling.

Before using this product refer to container label and HENKEL TECHNOLOGIES MATERIAL SAFETY DATA SHEET for additional precautionary, handling and first aid information.

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Rev. 9/2013

Henkel Corporation Aerospace | 2850 Willow Pass Road | Bay Point, CA 94565
PHONE: +1.925.458.8000 | FAX: +1.925.458.8030 | www.henkel.com/aerospace

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

