



LOCTITE EF 562 AERO

Foaming Core Splice Adhesive

(KNOWN AS Hysol MA 562)

INTRODUCTION

LOCTITE EF 562 AERO is a general purpose 250°F (121 °C) or 350°F (177 °C) curing foaming adhesive. LOCTITE EF 562 AERO is designed for service temperatures from -67°F (-55 °C) to 350°F (177 °C).

FEATURES

- Cured adhesive exhibits uniform cell structure upon cure; limits moisture ingress into splice area
- Qualified to many industry specifications
- Asbestos Free
- Dual cure capabilities at 250°F (121 °C) or 350°F (177 °C)
- Excellent slump resistance
- Low exothermic properties - ideal for thick splices or co-cure conditions

USES

- Sealing, splicing or reinforcing honeycomb core edge closeouts

Typical Technical Data	LOCTITE EF 562 100M AERO
Type:	Unsupported expandable epoxy film adhesive between liners of paper
Color:	Yellow
Volatiles:	<1%
Thickness:	0.050" & 0.100" (1.3 mm and 2.5mm)
Form:	1' x 2' sheets (~.3 x .6m)
Slump:	Less than 0.125" (3.18mm)
Expansion:	2 to 3.5 times original uncured thickness
Exotherm:	<550°F (280 °C) based on .200" (5.1mm) thick material
Cured Density:	25 to 35 lbs/cu. ft. (0.40-0.56 g/cc)
Shelf Life:	6 months @ 0°F (-18 °C) or below
Out Time:	10 days @ 90°F (32 °C) or 20 days @ 75°F (24 °C)

Application Method

Remove adhesive material from cold storage. Allow stabilization at room temperature. Keep the material wrapped to prevent moisture from condensing on the adhesive. Be sure parts to be bonded have been thoroughly cleaned and dried before bonding.

Cut adhesive to part size, remove the paper separator and apply to edge of honeycomb core. Remove the other paper and join to the other section of core or edge member. Assemble panel using desired adhesive. Panel is now ready for a cure in a press, vacuum bag in an oven, or an autoclave. Co-cure with panel adhesive.





LOCTITE EF 562 AERO

Foaming Core Splice Adhesive

(KNOWN AS Hysol MA 562)

Curing Conditions: 60 minutes at 250°F (121 °C) or 350°F (177 °C) with a heat up rate of 5-10°F (3-6 °C) per minute.

Clean-up

Uncured adhesive may be removed effectively with ketone solvents in well ventilated areas. Avoid contaminating uncured parts. Consult solvent container label/MSDS for proper safety and handling procedures.

Storage

The shelf life of LOCTITE® EF 562 AERO is 6 months at 0°F (-18 °C).
This product has an out time of 10 days @ 90°F (32 °C).

Performance Properties

Tube Shear Test Conditions ¹		Cured 60 Minutes @		Cured 60 Minutes @	
		250°F	121°C	350°F	177°C
Adhesive Thickness→		.050"	1.33mm	.050"	1.3mm
°F	°C	psi	MPa	psi	MPa
-67	-55	990	6.9	800	6.6
75	24	1200	8.3	1150	8.0
180	82	1240	8.6	1170	8.1
250	121	1150	8.0	1050	7.3
350	177	350	2.4	350	2.4

77°F (25°C) Tube Shear after Environmental Conditioning	Cured 60 Minutes @	
	250°F	121°C
	psi	MPa
15 minutes trichlorethane degreasing and 30 minutes @ 250°F (121 °F)	1080	7.5
7 days Skydrol @ 155°F (68 °C)	1085	7.5
3 day water boil	1095	7.5
30 day salt spray	780	5.4

1. Tube shear specimens were fabricated from P2 etched 5052 aluminum. Tube dimensions were 9" x 1" x 0.49" (228.6mm x 25.4mm x 1.24mm) and 9" x 0.5" x 0.49" (228.6mm x 12.7mm x 1.24mm). Tubes were loaded with 44.5 grams of LOCTITE EF 562 100M AERO.





LOCTITE EF 562 AERO

Foaming Core Splice Adhesive

(KNOWN AS Hysol MA 562)

Performance Properties (Continued)

Flexural Strength (ASTM C393) after 10 Minutes	77-250°F (25-121°C) for 1 Hour		77-350°F (25-177°C) for 1 Hour	
	psi	MPa	psi	MPa
@ -67°F (-55 °C)	730	6.07	740	5.14
@ 75°F (24 °C)	830	6.76	770	5.35
@ 180°F (82 °C)	750	6.21	760	5.28
@ 250°F (121 °C)	650	4.51	660	4.58
@ 250°F (121 °C)	710	4.93	-	-
@ 300°F (149 °C)	-		640	4.45
@ 350°F (177 °C)			540	3.75
@ 350°F (177 °C)			380	2.64
@ 425°F (208 °C)			140	0.97

Handling Precautions

Do not handle or use until the Material Safety Data Sheet has been read and understood. For industrial use only.

DISPOSAL INFORMATION

Dispose of spent remover and paint residue per local, state and regional regulations. Refer to HENKEL TECHNOLOGIES MATERIAL SAFETY DATA SHEET for additional disposal information.

PRECAUTIONARY INFORMATION

General:

As with most epoxy based systems, use this product with adequate ventilation. Do not get in eyes or on skin. Avoid breathing the vapors. Wash thoroughly with soap and water after handling.

Before using this product refer to container label and HENKEL TECHNOLOGIES MATERIAL SAFETY DATA SHEET for additional precautionary, handling and first aid information.





LOCTITE EF 562 AERO

Foaming Core Splice Adhesive

(KNOWN AS Hysol MA 562)

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Rev. 9/2013

Henkel Corporation Aerospace | 2850 Willow Pass Road | Bay Point, CA 94565
PHONE: +1.925.458.8000 | FAX: +1.925.458.8030 | www.henkel.com/aerospace

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

